



Qualipur[®] 1030

Features and Benefits

- ✓ One Component
- ✓ Spray or Rolled Applied
- ✓ Low Viscosity
- ✓ Optimal Penetration

1. General Description

Qualipur 1030 is a one component, solvent based polyurethane primer.

Basic Uses: Qualipur 1030 is designed for priming bituminous surfaces prior to the application of polyurethane bound rubber granule elastic layers.

2. Safety Guidelines

Always wear the recommended personal protective equipment. Avoid contact with eyes, skin, and clothing. Adequate ventilation is required during the application process.

3. Storage and Packaging

Qualipur 1030 should be kept dry and cool. Storage temperature should be between 5°C (40°F) and 66°C (150°F). Do not expose container to open flame, excessive heat, or direct sunlight.

Product shelf life is 1 year in original sealed container.

Qualipur 1030 is packaged at 180 kg (approximately 47 gallon).

4. Coverage

The consumption rate is 0.150 – 0.200 kg/m² (0.277 – 0.369 lb/yd²).

5. Installation Guidelines

The surface to be primed must be clean, dry, and free of oil, grease, dirt, and any foreign residue. Qualipur 1030 is ready for use; therefore, diluting is not recommended.

In order to obtain uniform coverage, the preferred application method is with an airless spray machine. Qualipur 1030 can also be applied with a roller. Primed surfaces are ready for the next coat once a film has formed.



6. Limitations

- Do not apply over wet or damp substrates
- Do not apply to surfaces with active moisture vapor transmission
- Do not apply in thick layers
- Primed surface should be coated within 24 hours
- Substrate and application minimum temperature: 10°C (50°F)
- Substrate and application maximum temperature: 60°C (140°F)
- Permissible relative humidity: 40 – 90%

7. Technical Data

VOC Content		92 g/L*
Renewable Content		1.62%
Density	23°C (73°F)	0.95 – 1.05 g/cm ³
Run Out Time	23°C (73°F)	38 – 48 seconds
Color		Clear/Pale Yellow
Recoat Time	23°C (73°F)	2 – 4 hours

*Based on Standard formula calculation

Above figures are guide values and should not be used as a base for specifications

Consult the Safety Data Sheet for more details

For complete and latest warranty and product information, please visit www.advpolytech.com

