



# Qualipur<sup>®</sup> 552 E

## 1. General Description

Qualipur 552 E is a 2-component, epoxy coating. Qualipur 552 E is ideal for a primer coat, intermediate coat, and topcoat flooring system as this product has excellent tensile strength and good chemical resistance properties.

Basic Uses: A highly abrasion-resistant intermediate coat and top coat.

Colors: A gloss finish product available in 5 standard colors: Light Grey, Dark Grey, Charcoal, Tan, and Black. Special colors are available upon request.

## 2. Safety Guidelines

Always wear the recommended personal protective equipment. Avoid contact with eyes, skin, and clothing. Adequate ventilation is required during the application process.

Do not expose container to open flame, excessive heat, or direct sunlight.

## 3. Storage and Packaging

Qualipur 552E should be stored in a clean, cool, dry area in original unopened pail. Qualipur 552E has a shelf life of 1 year.

Packaging: 5 gallon unit (21.39 kg unit).

## 4. Coverage

For reference 1 mil of Qualipur 552 E has a consumption rate of 1493 sqft/gallon (0.00067 gal/ft<sup>2</sup> or 0.0287 kg/m<sup>2</sup>). Typical application is 15 mils and has a consumption rate of 107 sqft/gal (0.0101 gal/ft<sup>2</sup> or 0.4305 kg/m<sup>2</sup>).

## 5. Installation Guidelines

### Surface Preparation:

See Qualideck Application Guide

A surface receiving an application of Qualipur 552 E must be clean, sound, dry, and free of oils and all bond inhibiting compounds and contaminants. Apply Qualipur 552 E as primer for concrete or on Qualipur urethane surfaces that have received the recommended surface preparation (sandblasting

## Features and Benefits

- ✓ Epoxy coating
- ✓ High abrasion and cut/tear resistance
- ✓ Wide range of system options and textures
- ✓ Excellent tensile strength
- ✓ Good chemical resistant properties



or shot blasting are recommended to produce a clean and lightly textured surface). When top coating a system, if the recommended recoat time is exceeded or if contamination of the substrate occurs, consult your sales representative.

## Mixing:

Pre-mix the color component. Then, empty the contents of component “B” into component “A”. Mixing is accomplished by using a jiffy paddle and low speed drill (400 to 600 rpm). Take care not to incorporate excessive air into the product. Mix components for 2 minutes in provided pail. Scrape down sides of pail and mix for additional 1.5 minutes before proceeding with application.

## Application:

See Qualideck Application Guide

## 6. Limitations

- Minimum application temperature is 40°F and rising.
- Do not apply over damp or wet substrates.
- Do not apply to surfaces with active moisture vapor transmission.

## 7. Technical Data

*Results based on temperature of 68°F and 50% Humidity*

VOC		85 g/L*
Viscosity	ASTM D2196	1200 - 1600 cPs
Pot Life	ASTM C603	42 - 62 Minutes
Cure Time – Tack Free		4 – 6 Hours
- Foot Traffic	ASTM C920	24 Hours
- Final Cure		7 Days
Elongation	ASTM D412	8%
Tensile Strength	ASTM D412	11,920 PSI
Hardness	ASTM D2240	75 D scale
Skid Resistance Dry		Pass
Skid Resistance Wet		Pass
Abrasion Resistance	ASTM D4060	46.2 mg loss
Flash Point	ASTM D93	Non Flammable

\*based on standard formula calculation





## Chemical Resistance Chart

Chemical	Qualipur 372	Qualipur 461	Qualipur 512	Qualipur 522	Qualipur 552E	Qualipur 582
Acetic Acid 10%	-	-	+	+	-	+
Acetic Acid 50%	-	-	-	+	-	-
Acetone	+	+	+	+	+	-
Anti-Freeze	+	+	+	+	+	+
Bleach	-	+	+	+	+	+
Brake Fluid	-	-	-	-	-	-
Caustic Soda	+	+	-	+	+	+
Gasoline	+	+	+	+	+	-
Hydraulic Fluid	+	+	+	+	+	+
Hydrochloric Acid 10%	-	-	-	+	+	+
Hydrochloric Acid 31%	-	-	-	-	-	-
Jet Fuel	+	+	+	+	+	+
Methanol	+	+	+	+	-	-
Mineral Spirits	+	+	+	+	+	+
Motor Oil	-	+	-	+	+	+
Phosphoric Acid 50%	+	-	-	+	-	-
Phosphoric Acid 70%	-	-	-	-	-	-
Potassium Hydroxide 50%	-	-	-	-	+	+
Simple Green	+	+	+	+	+	+
Skydrol	-	-	-	+	-	-
Sodium Hydroxide 50%	+	+	+	+	+	+
Sulfuric Acid 25%	-	-	-	-	-	-
Sulfuric Acid 50%	-	-	-	-	-	-

(-) --> Visual Defects Observed

(+) --> No Visual Defects Observed

*Above figures are guide values and should not be used as a base for specifications*

*Consult the Safety Data Sheet (SDS) for more details.*

*For complete and latest warranty and product information, please visit [www.advpolytech.com](http://www.advpolytech.com)*

